



12 **EUROPEAN PATENT SPECIFICATION**

46 Date of publication of patent specification :
24.02.93 Bulletin 93/08

51 Int. Cl.⁵ : **F16L 59/08, F16L 59/04,
F16L 59/06**

21 Application number : **90308459.8**

22 Date of filing : **31.07.90**

54 **Thermal insulation.**

30 Priority : **09.08.89 GB 8918218**

73 Proprietor : **The BOC Group plc
Chertsey Road
Windlesham Surrey GU20 6HJ (GB)**

43 Date of publication of application :
13.02.91 Bulletin 91/07

72 Inventor : **Garrett, Michael Ernest
92 York Road
Woking, Surrey (GB)**

45 Publication of the grant of the patent :
24.02.93 Bulletin 93/08

84 Designated Contracting States :
BE DE GB NL

74 Representative : **Wickham, Michael et al
c/o Patent and Trademark Department The
BOC Group plc Chertsey Road
Windlesham Surrey GU20 6HJ (GB)**

56 References cited :
**DE-A- 2 333 933
DE-A- 3 237 877
DE-A- 3 240 664**

EP 0 412 715 B1

Note : Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

The polyurethane coating 8 has a thickness of 2.5 cm. It contains closed cells which at ambient temperature are filled with carbon dioxide gas. The pipe 2 is located in an outer sleeve 10. The annular space between the inner surface of the sleeve 10 and the coated outer surface 6 of the pipe 2 is filled with a mineral insulant powder such as perlite. The sleeve 10 is provided with an inlet and an outlet (not shown) whereby the perlite-filled space may be intermittently or continuously purged with dry nitrogen gas.

In order to form the apparatus shown in the drawing the pipe is first coated with the polyurethane using carbon-dioxide as a blowing gas. A conventional spray gun may be used for this purpose. The polyurethane adheres to the outer surface of the pipe 2 and forms a foamed cellular coating having closed pores containing carbon dioxide gas. The sleeve 10 is then fitted around the pipe 2 and the annular space therebetween filled with the perlite insulant. The annular space is then purged with nitrogen to flush air therefrom. If desired, once the air has been purged from the annular space, the flow of nitrogen may be continued or alternatively can be stopped and then the space purged only intermittently with nitrogen. The pipeline may then be brought into service. One use for the pipeline is to transmit helium at a temperature of 70K from a source thereof to a chamber which needs to be maintained at 70K for superconductors located therein to function properly. As the helium flows along pipeline 2 so the temperature of the carbon dioxide in the pores of the foamed polyurethane falls. At about 190K the carbon dioxide condenses to form a solid. Consequently, the pressure within the individual cold pores is much reduced as a result of the reduction in the volume occupied by the carbon dioxide upon its solidification. The pressure tends to fall further with decreasing temperature. Accordingly, a vacuum-insulated foam is created close to the cold wall of the pipe 2. Consequently, the heat leak through this foam is by conduction through the plastics material itself and is therefore quite low. This has the effect of raising the temperature of the outer surface of the foam to be above the nitrogen condensation point of 77K, thereby enabling the conventional perlite thermal insulant (or other thermally insulating material) to be employed in the remaining insulating space.

Although the material of the foam is organic, it will not create a fire or explosion hazard because the only gas in contact with it is nitrogen which is itself inert. In the event of the foam cracking or failing, nitrogen will condense with loss of insulating properties but no further problems. If desired, after a chosen time in service, the pipeline may be taken out of service, the polyurethane coating removed and a new coating applied. The duration of service can be chosen so as to enable a new coating to be applied before the old one fails.

The method of apparatus according to the invention make possible an effective and efficient insulation at temperatures in the order of 70K without the need for conventional vacuum insulation.

Claims

1. Thermally-insulated apparatus including a wall one side (4) of which is in contact with a cryogenic medium and the other side (6) of which has adhering thereto foamed material (8) characterised in that the foamed material (8) defines closed cells containing a substance which is gaseous at normal ambient temperatures and solid at temperatures of 77K and less, the foamed material (8) facing a space which contains thermal insulation and a nitrogen atmosphere.
2. Apparatus as claimed in claim 1, in which the foamed material is a foamed plastics.
3. Apparatus as claimed in claim 1 or claim 2, in which the gas contained within the cells of the foamed material is carbon dioxide.
4. Apparatus as claimed in any one of the preceding claims, in which the foamed material is in a layer that is at least 0.3 centimetres thick.
5. Apparatus as claimed in any one of the preceding claims, in which the thermal insulant is a mineral powder.
6. A method of thermally insulating a wall which on one side is to be exposed to a medium at a temperature of less than 77K, comprising the steps of coating the wall with a foamed material having closed cells containing a gas which is solid at temperatures of 77K or less, forming an enclosure containing thermal insulant about said wall, subjecting the inner surface of said wall to cryogenic medium whereby to reduce its temperature to below 77K, and purging the enclosure with dry nitrogen, whereby the cryogenic medium causes the gas within the cells of the foamed material to solidify thus creating a partial vacuum therein which is effective to prevent the outer surface of the foamed material reaching so low a temperature that the nitrogen purge gas condenses thereon.
7. A method as claimed in claim 6, in which the foamed material is a foamed plastics.
8. A method as claimed in claim 6 or claim 7, in which the gas contained within the cells of the foamed material is carbon dioxide.

9. A method as claimed in claim 8, in which the thickness of the foamed layer is in the range 0.3 to 3 centimetres.
10. A method as claimed in any one of claims 6 to 9, in which the thermal insulant is a mineral powder.

Patentansprüche

1. Wärmeisolierte Vorrichtung mit einer Wand, deren eine Seite (4) sich in Kontakt mit einem kryogenen Medium befindet und deren andere Seite (6) ein an dieser haftendes, geschäumtes Material (8) aufweist, dadurch gekennzeichnet, daß das geschäumte Material (8) geschlossene Zellen definiert, die eine Substanz enthalten, welche bei normalen Umgebungstemperaturen gasförmig und bei Temperaturen von 77K und weniger fest ist, wobei das geschäumte Material (8) einem Raum zugewandt ist, der eine Wärmeisolierung und eine Stickstoffatmosphäre enthält.
2. Vorrichtung nach Anspruch 1, bei der das geschäumte Material ein geschäumter Kunststoff ist.
3. Vorrichtung nach Anspruch 1 oder 2, bei der das in den Zellen des geschäumten Materials enthaltene Gas Kohlendioxid ist.
4. Vorrichtung nach einem der vorhergehenden Ansprüche, bei der das geschäumte Material in einer Schicht vorliegt, die zumindest 0,3 cm dick ist.
5. Vorrichtung nach einem der vorhergehenden Ansprüche, bei der der Wärmeisolierstoff ein Mineralpulver ist.
6. Verfahren zum Wärmeisolieren einer Wand, die an einer Seite einem Medium mit einer Temperatur von weniger als 77K ausgesetzt werden soll, mit den Schritten, daß die Wand mit einem geschäumten Material beschichtet wird, das geschlossene Zellen aufweist, die ein Gas enthalten, welches bei Temperaturen von 77K und weniger fest ist, daß eine einen Wärmeisolierstoff enthaltende Umhüllung um die Wand gebildet wird, daß die innere Oberfläche der Wand einem kryogenen Medium ausgesetzt wird, wodurch ihre Temperatur auf unterhalb 77K gesenkt wird, und daß die Umhüllung mit trockenem Stickstoff gespült wird, wodurch das kryogene Medium das Gas in den Zellen des geschäumten Materials zum Erstarren bringt, so daß in diesen ein Teilvakuum erzeugt wird, das wirksam verhindert, daß

die äußere Oberfläche des geschäumten Materials eine so niedrige Temperatur erreicht, daß das Stickstoffspülgas darauf kondensiert.

7. Verfahren nach Anspruch 6, bei dem das geschäumte Material ein geschäumter Kunststoff ist.
8. Verfahren nach Anspruch 6 oder 7, bei dem das in den Zellen des geschäumten Materials enthaltene Gas Kohlendioxid ist.
9. Verfahren nach Anspruch 8, bei dem die Dicke der geschäumten Schicht im Bereich von 0,3 - 3 Zentimeter liegt.
10. Verfahren nach einem der Ansprüche 6 bis 9, bei dem der Wärmeisolierstoff ein Mineralpulver ist.

Revendications

1. Appareil isolé thermiquement comprenant une paroi dont un côté (4) est en contact avec un milieu cryogénique et sur l'autre côté (6) de laquelle adhère une matière en mousse (8), caractérisé en ce que la matière en mousse (8) définit des cellules fermées contenant une substance qui est gazeuse à des températures ambiantes normales et solide à des températures de 77K et moins, la matière en mousse (8) faisant face à un espace qui contient une isolation thermique et une atmosphère d'azote.
2. Appareil suivant la revendication 1, caractérisé en ce que la matière en mousse est une matière plastique mousse.
3. Appareil suivant l'une ou l'autre des revendications 1 et 2, caractérisé en ce que le gaz contenu à l'intérieur des cellules de la matière en mousse est du dioxyde de carbone.
4. Appareil suivant l'une quelconque des revendications précédentes, caractérisé en ce que la matière en mousse est sous la forme d'une couche qui a une épaisseur d'au moins 0,3 cm.
5. Appareil suivant l'une quelconque des revendications précédentes, caractérisé en ce que l'isolant thermique est une poudre minérale.
6. Procédé d'isolation thermique d'une paroi dont un côté doit être exposé à un milieu à une température de moins de 77K, comprenant les étapes qui consistent à revêtir la paroi d'une matière en mousse comportant des cellules fermées contenant un gaz qui est solide à des température de

- 77K et moins, à former une enceinte contenant un isolant thermique autour de ladite paroi, à soumettre la surface intérieure de cette paroi à un milieu cryogénique de manière à abaisser sa température en dessous de 77K, et à purger l'enceinte avec de l'azote sec, de telle sorte que le milieu cryogénique amène le gaz à l'intérieur des cellules de la matière en mousse à se solidifier, en y créant ainsi un vide partiel qui est efficace pour empêcher la surface extérieure de la matière en mousse d'atteindre une température tellement basse que le gaz de purge d'azote s'y condense.
- 5
- 10
7. Procédé suivant la revendication 6, caractérisé en ce que la matière en mousse est une matière plastique mousse.
- 15
8. Procédé suivant l'une ou l'autre des revendications 6 et 7, caractérisé en ce que le gaz contenu à l'intérieur des cellules de la matière en mousse est du dioxyde de carbone.
- 20
9. Procédé suivant la revendication 8, caractérisé en ce que l'épaisseur de la couche en mousse est de l'ordre de 0,3 à 3 cm.
- 25
10. Procédé suivant l'une quelconque des revendications 6 à 9, caractérisé en ce que l'isolant thermique est une poudre minérale.
- 30

35

40

45

50

55

5

